Description

2-mil, premium PVC-free and plasticizer-free high performance laminating film, transparent with glossy surface and highest level of UV protection.

Release Liner

1.4-mil polyester film, silicone-coated on one side

Adhesive

Clear, solvent-based, permanent

Area of Use

For protection of digitally printed large format images in indoor and outdoor graphic applications. Recommended for use with PVC-free and plasticizer-free digital printing film ORAJET[®] 3981RA PVC-Free Wrapping Film with *Rapid*Air[®] technology.

Technical Data

Thickness (without liner and adhesive)	2-mil
Dimensional Stability (FINT TM 14)	Adhered to steel, shrinkage 0.003 max.
Temperature Resistance	Adhered to aluminum, -58°F to +212°F, no variation
Adhesive Power (FINAT TM-1, after 24 h, average)	Adhered to stainless steel: 2.74 lb/in
Tensile Strength (DIN EN ISO 527)	Along: Min. 25 MPa Across: Min. 25 MPa
Elongation at Break (DIN EN ISO 527)	Along: Min. 150% Across: Min. 150%
Seawaterability (DIN 50 021)	Adhered to aluminum, after 100h/73°F, no variation
Resistance to Solvents and Chemicals	At room temperature, 72h after adhesion to aluminum, short-term resistant to most oils and greases, fuels, aliphatic solvents, weak acids, salts and alkalis
Shelf Life (68°F/50% relative humidity)	2 years
Minimum Life Expectancy (based on accepted application procedures on vertical surfaces, normal climate of Central Europe)	10 years
Minimum Application Temperature	> +46°F
Available Lengths Available Widths	150' (50-yard), 30' (10-yard) 54", 60"
Recommended to be used in combination with	ORAJET [®] Series 3981RA
UV Protection Extension Factor	+ 4 Years
For best results, utilize ORAFOL ICC profiles available at www.ora	folamericas com and allow solvent-based inks to dry for at least 24 hours

For best results, utilize ORAFOL ICC profiles available at www.orafolamericas.com and allow solvent-based inks to dry for at least 24 hours (48-72 hours preferred) at 70°F before cutting the graphic to the ink or applying a laminate.

Note

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be completely cured. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Films with structured surface are naturally more sensitive than the unstructured. Accordingly, these films are to be treated carefully both in processing and in cleaning. Impurities affect the appearance of structured films and require more frequent cleaning. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.



ORAFOL Americas – GA 1100 Oracal Parkway Black Creek, GA 31308 Phone: 888.672.2251

ORAFOL Americas - CTORAFOL Canada120 Darling Drive2831 Bristol CircleAvon, CT 06001Oakville, Ontario L6H 6X5Phone: 800.654.7570Phone: 888.727.3374techsupport-americas@orafol.com- www.orafolamericas.com

IMPORTANT NOTICE

All ORAGUARD[®] products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORAGUARD[®] products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORAGUARD[®] products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice.

WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects or other reproductive harm.



ORAFOL Americas – GA 1100 Oracal Parkway Black Creek, GA 31308 Phone: 888.672.2251

ORAFOL Americas - CTORAFOL Canada120 Darling Drive2831 Bristol CircleAvon, CT 06001Oakville, Ontario L6H 6X5Phone: 800.654.7570Phone: 888.727.3374techsupport-americas@orafol.com - www.orafolamericas.com