

ORAJET® 3164

SOFT CALENDERED PVC DIGITAL MEDIA

Technical Datasheet
02/15
Page 1 of 2

Description

4-mil, soft calendered PVC film in white with a gloss or matte surface and in transparent with a gloss surface. UL certified for UL 969 "Marking and Labeling Systems" (USA) and CSA C22.2 No. 0.15 "Adhesive Labels" (Canada).

Release Liner

83# PE coated silicone paper

Adhesive

Clear, water-based, permanent adhesive

Area of Use

For economical general signage, short- to medium-term flat indoor and outdoor applications including decals, nameplates, die cut letters and POP displays.

Technical Data

Thickness (without liner and adhesive)	4-mil	
Dimensional Stability (FINAT TM-14)	Adhered to steel, no shrinkage in cross direction; In length, <.016"	
Temperature Resistance	Adhered to aluminum, -40°F to +176°F, no variation	
Fire Behavior (DIN 75200)	Adhered to steel, self-extinguishing	
Fire Rating	ASTM E 84-07 Class "A"	
Adhesive Power (FINAT TM-1, after 24 h, average)	Adhered to stainless steel: 3.7 lb/in	
Tensile Strength (DIN EN ISO 527)	Along: Min. 19 MPa Across: Min. 19 MPa	
Elongation at Break (DIN EN ISO 527)	Along: Min. 130% Across: Min. 150%	
Seawaterability (DIN 50 021)	Adhered to aluminum, after 100h/73°F, no variation	
Shelf Life (68°F/50% relative humidity)	2 years	
Minimum Life Expectancy (based on accepted application procedures on vertical surfaces)	4 years (unprinted)	
Minimum Application Temperature	50°F	
Available Lengths	<u>White</u> 150' (50-yard)	<u>Transparent</u> 150' (50-yard)
Available Widths	30", 50", 54", 60", 80"	54"
Recommended Laminates	ORAGUARD® Series 200, 210	
Print Compatibility	Latex, Solvent, Eco-Solvent, UV Curable	

For best results, utilize ORAFOL ICC profiles available at www.orafolamericas.com and allow solvent-based inks to dry for at least 24 hours (48-72 hours preferred) at 70°F before cutting the graphic to the ink or applying a laminate.

Note

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be completely cured. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Films with structured surface are naturally more sensitive than the unstructured. Accordingly, these films are to be treated carefully both in processing and in cleaning. Impurities affect the appearance of structured films and require more frequent cleaning. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.



ORAFOL Americas – GA
1100 Oracal Parkway
Black Creek, GA 31308
Phone: 888.672.2251

ORAFOL Americas – CT
120 Darling Drive
Avon, CT 06001
Phone: 800.654.7570
techsupport-americas@orafol.com

ORAFOL Canada
2831 Bristol Circle
Oakville, Ontario L6H 6X5
Phone: 888.727.3374

www.orafolamericas.com

ORAJET® 3164

SOFT CALENDERED PVC DIGITAL MEDIA

Technical Datasheet
02/15
Page 2 of 2

IMPORTANT NOTICE

All ORAJET® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORAJET® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORAJET® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use.

All specifications are subject to change without prior notice.

WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects or other reproductive harm.



ORAFOL Americas – GA
1100 Oracal Parkway
Black Creek, GA 31308
Phone: 888.672.2251

ORAFOL Americas – CT
120 Darling Drive
Avon, CT 06001
Phone: 800.654.7570

ORAFOL Canada
2831 Bristol Circle
Oakville, Ontario L6H 6X5
Phone: 888.727.3374

techsupport-americas@orafol.com – www.orafolamericas.com